

Technical data sheet

CTS-N690C Acrylic Polymer in Primary Forms

This series of products applicable to all types of high-grade windbreaker cloth, umbrella cloth and other high-grade fabric printing.

Characteristics :

high fastness, not sticky, excellent operation.

Reference ratio:

Product/color	White or light	Medium	Deep
CTS-N690 W	80-100%	40-50%	0-20%
CTS-N690 C	0-20%	50-60%	80-100%
CTS-N690B	98%	98%	98%
CT-31 fixer	1-2%	1-2%	1-2%
Mesh No.	43-48T	43-48T	43-48T

Technological process:

Print CTS-N690B for under based 2-3times.

Directly printing color 3 times → finished product .

Curing Process:

Temperature:130℃ with 90s.

Suggestions:

- 1 for color rate, do not exceed the normal standard(5-7%);
- 2, test shall ensure that the stamp is completely dry, otherwise it will affect the test results;
- 3, if not after heat treatment, to achieve the best effect of this product, recommended CT-31 and other additives, to accelerate the cross-linking rate or extend the natural air dry time.

In verbal or written just the technical advice to show our Companies sincerity, but for our products ,the user companies still have your responsibility for test, to verify whether is suitable for the process and to use; Given the use of the products of our company process conditions are not my company control, and therefore should be fully responsible by the users themselves.